

## IMPERDAN FP 40 P

IMPERDAN FP 40 P is a waterproofing bituminous sheet with non self-protected surface of 4.0 kg/m<sup>2</sup>, LBM-40-FP (APP -5 °C).

Composed of a non-woven polyester felt reinforcement and covered on both sides with polymer modified bitumen (pliability -5°C) mastic. A polyethylene film is used as anti-adherent material on both sides.

Tested according to standard EN test methods.



### CE MARKING



Identification number of the Certification Body: 1035

DERIVADOS ASFALTICOS NORMALIZADOS S.A.  
Calle La Granja 3 (28108 - Alcobendas, MADRID)

Year in which the CE marking was affixed: 2009  
Certificate number CPF: 1035-CPD-ES044104  
European standard EN 13707

Produced at: Poligono Industrial Sector 9 (19290 - FONTANAR, Guadalajara)

Membrane of 1 m x 10 m x 4.0 kg/m<sup>2</sup> composed of polymer modified bitumen (pliability -5°C) with non-woven polyester felt. Both sides are protected by a thermofusible film. Torch-on application.

TECHNICAL DATA	VALUE	UNIT	STANDARD
External fire performance	PND	-	UNE-EN 1187; UNE-EN 13501-5
Reaction to fire	E	-	UNE-EN 11925-2; UNE-EN 13501-1
Watertightness	Pasa	-	UNE-EN 1928
Longitudinal tensile strength	700 ± 200	N/5cm	UNE-EN 12311-1
Transversal tensile strength	450 ± 150	N/5cm	UNE-EN 12311-1
Longitudinal elongation at break	45 ± 15	%	UNE-EN 12311-1
Transversal elongation at break	45 ± 15	%	UNE-EN 12311-1
Resistance to root penetration	No Pasa	-	EN 13948
Resistance to static loading	>15	kg	UNE-EN 12730
Resistance to impact	>1000	mm	UNE-EN 12691
Longitudinal resistance to tearing (nail shank)	220 ± 40	N	UNE-EN 12310-1
Transversal resistance to tearing (nail shank)	220 ± 40	N	UNE-EN 12310-1
Joint strength: peel resistance	PND	-	UNE-EN 12316-1
Joint strength: shear resistance	450 ± 150	-	UNE-EN 12317-1
Flexibility at low temperature	< -5	°C	UNE-EN 1109
Humidity resistance factor	20.000	-	UNE-EN 1931
Dangerous substances	PND	-	-
Flexibility at low temperature (pliability)	0 ± 5	°C	UNE-EN 1109
Flow resistance at elevated temperature	120 ± 10	°C	UN-EN 1110

Pasa = Positive or correct    No pasa = Negative    PND = No performance determined    - = Not necessary

**ADDITIONAL TECHNICAL DATA**

ADDITIONAL DATA	VALUE	UNIT	STANDARD
Mass per unit area (nominal)	4.0	kg/m <sup>2</sup>	-
Mass per unit area (minimum)	3.8	kg/m <sup>2</sup>	-
Nominal thickness	3.3	mm	-
Flow resistance at elevated temperature	>130	°C	UN-EN 1110
Dimensional stability at elevated temperature (longitudinal)	< 0.6	%	UNE-EN 1107-1
Adhesion of granules	PND	%	UNE-EN 12039

Membranes thickness tolerance: = -0,3 mm, apart from membranes with thickness 2 and 2,4 mm whose tolerance is = -0,2 mm.  
 Membranes mass per unit area tolerance: -5% (mini) and +10% (maxi) from nominal value.

**DECLARATION OF CONFORMITY**


DERIVADOS ASFÁLTICOS NORMALIZADOS S.A.  
 Calle La Granja 3 (28108 - Alcobendas, MADRID)

Membrane of 1 m x 10 m x 4.0 kg/m<sup>2</sup> composed of polymer modified bitumen (pliability -5°C) with non-woven polyester felt. Both sides are protected by a polyethylene film. Torch-on application.

This product is according to the Z.A. Annex of the UNE-EN 13707.  
 The roll must be stored upright and protected against atmospheric conditions and dampness. The Application cannot be done under temperatures lower than 0 °C.

Certificate number CPF: 1035-CPD-ES044104


José Antonio Manzarbeitia Valle  
 Manager Quality and R&D Manager.  
 Fontanar, March 01st 2009

**STANDARDS AND CERTIFICATION**

UNE EN 13707 standard.  
 CE marking.

**PRESENTATION**

PRESENTATION	VALUE	UNIT
Length	10	m
Width	1	m
Roll surface	10	m <sup>2</sup>
Rolls per pallet	23	rolls
Product Code	141804	-



1. polyethylene film
2. polymer modified bitumen (pliability -5°C)
3. non-woven polyester felt

**WARNING**

The information that appears in the following document makes reference to the uses and utilities of danosa's products and systems, and it is based on the knowledge that have been learnt until present, by Danosa. This is only possible if products have been stored and used in an appropriate way.

Nevertheless, Danosa is not responsible for unsuitable uses of the products neither any other facts, such as meteorological facts. So Danosa is just responsible for the quality related to the provided products.

Danosa reserves the right to carry out modifications without previous notice.

The values that appear in the technical sheet are the results of the tests that have been performed in our laboratory. March 2012.

Web site: [www.danosa.com](http://www.danosa.com) E-mail: [export@danosa.com](mailto:export@danosa.com) Phone number: +34 949 888 210